



SHINWA SANGYO CO.,LTD.

2-15-18 Ainokawa, Ichikawa-Shi, Chiba-ken, Japan, 272-0143

Phone: +81-47-356-3281

FAX: +81-47-356-3288

Jewelry Wax from SHINWA SANGYO CO.,LTD.

Product name	RP-194	RP-206	RP-294
Photo			
Color	Pink / Red	Blue-green / Yellow	Purple / Dark purple
Softening Point °C	69	69	69
Congeaing Point °C	60	61	61
Molding temperature	70~	70~	70~
Density g/cc	0.93	0.93	0.93
Ash %	0	0	0
Viscosity mPa·s			
at 80 °C	119	212	343
at 75 °C	139	252	423
at 70 °C	165	306	505
at 65 °C	215	367	607
Comment	<ul style="list-style-type: none"> ▪ especially good flowability ▪ best for reproduction of fine design 	<ul style="list-style-type: none"> ▪ good fluidity and reproducibility ▪ balanced general purpose wax 	<ul style="list-style-type: none"> ▪ small shrinkage ▪ best for large size pattern