

[Paraffin Wax]

Grade Item		155/160°F ASTM	150/155°F ASTM	140/145°F ASTM	EP 140/145°F ASTM	135/140°F ASTM	130/135°F ASTM	125/130°F ASTM	120/125°F ASTM	115/120°F ASTM
Melting Point (ASTM D87)	°C (°F)	69.3 (157)	66.5 (152)	61.3 (142)	61.7 (143)	58.7 (138)	56.7 (134)	52.6 (127)	49.4 (121)	47.2 (117)
Oil Content (ASTM D721)	mass%	0.2	0.2	0.2	0.2	0.3	0.3	0.3	0.3	0.5
Color Saybolt (ASTM D156)		+30	+30	+30	+30	+30	+30	+30	+30	+30
Penetration (ASTM D1321)	0.1 mm at 25°C at 35°C	13 18	14 19	11 17	12 19	12 20	13 18	17	20	30
Specific Gravity	g/cm ³ at 70°C	0.783 at 80°C	0.779 at 80°C	0,777	0,779	0,775	0,774	0,771	0,769	0,769
Odor & Taste		Nil	Nil	Nil	Nil	Nil	Nil	Nil	Nil	Nil
Flash Point (C. O. C) (ASTM D92)	°C	264	261	236	235	234	220	212	212	202
Ultraviolet Absorbance	FDA 172, 886 FDA 178, 3710	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass

APPLICATION:

Hotmelt Adhesives	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>						
Paper Cups			<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>			
Plastics Lubricants	<input type="radio"/>	<input type="radio"/>								
Paper Converting	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>			
Rubber Antiozonant	<input type="radio"/>	<input type="radio"/>		<input type="radio"/>	<input type="radio"/>					
Polish			<input type="radio"/>	<input type="radio"/>	<input type="radio"/>					
Cosmetic & Pharmaceutical	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>			<input type="radio"/>			
Candles			<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>				
Water-Proof Corrugated Paperboard					<input type="radio"/>	<input type="radio"/>	<input type="radio"/>			
Chlorinated Paraffin							<input type="radio"/>	<input type="radio"/>		
Matches							<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	
Rust Preventive								<input type="radio"/>	<input type="radio"/>	
Plywood							<input type="radio"/>	<input type="radio"/>	<input type="radio"/>	
Textiles						<input type="radio"/>	<input type="radio"/>	<input type="radio"/>		